



TA02 THIN-SET MORTAR WITH POLYMER

DS-EN-TA02-20170427

PRODUCT NAME

TA02 Thin-Set Mortar with Polymer

COLOR

Grey or White

MANUFACTURER

TM Building System Canada Limited

2525 Tedlo St. Mississauga, Ontario, L5A 4A8,
Canada

Tel: 905-275-7545

Fax: 905-275-7025

Website: www.tammycanada.com

PRODUCT DESCRIPTION

TA02 is a premium blend of admixtures incorporated in a mix of Portland cement and selected aggregates, yielding a quality thinset mortar of high bond strength with a smooth application.

FEATURES AND BENEFITS

- Exceeds ISO13007 C1 standard
- Exceeds ANSI A118.4 bond strength requirements
- Easy to use, just mix with water
- High bond strength
- Green environmental protection

USES

- Various types of ceramic tiles, large areas of glass enamel and non-enamel clay tiles
- Interior and exterior

SUITABLE SUBSTRATES

- Concrete
- Cement plaster and mortar

- Existing ceramic tile and stone

PACKAGING

22.7kg/ bag (50 lb/bag)

APPROXIMATE COVERAGE

Notch Size (Inches)	Approx. Coverage
---------------------	------------------

1/4x1/4x1/4-Square	80 sq.ft.(7.5 sq.m)
--------------------	---------------------

1/4x3/8x1/4-Square	65 sq.ft.(6 sq.m.)
--------------------	--------------------

Trowel Notches -Width x Depth x Space Apart

SHELF LIFE

Storage temperature range between 5°C and 35°C, in dry and cool area, the product shelf life in factory sealed containers is 12 months..

* High humidity will reduce the shelf life of bagged products.

LIMITATIONS AND CAUTIONS

- Mixed mortar should be finished within 4 hours and stirring every half hour to keep well operability, cured mortar should be discarded.
- 24 hours after curing is needed before other installation (grouting).
- No watering allowed during and within 48 hours of installation
- Tools need to be cleaned immediately after application as it is difficult to clean after curing
- Keep out of reach of children



TECHNICAL DATA

PHYSICAL PROPERTIES

(Meets or exceeds ISO13007 C1 standard.)

Test	Testing Results	Specification
Original Tensile Adhesive Strength /MPa	0.7	≥ 0.5
Water Immersion Tensile Adhesive Strength /MPa	0.8	≥ 0.5
Freeze/Thaw Cycle Tensile Adhesive Strength /MPa	0.6	≥ 0.5
Open Time After 20 Minutes, Tensile Adhesive Strength /MPa	0.65	≥ 0.5

WORKING PROPERTIES

Mixing ratio	Powder : water =4.3:1 (weight ratio)
Product density	About 1400kg/ m ³
Open Time	20 minutes
Adjustment time	15 minutes
Pot life	2 hours
Time to Heavy Traffic	> 24 hours
Wet Density	About 1600kg /m ³

APPLICATION

TOOLS

Low-speed Mixer, Mixing Container, Notched Trowel, Leveler, Tile Vibrator, Sucker, Spacer, Towel, Tile cutter, Knife etc...

TILE AND SUBSTRATE PREPARATION

Inspect the back of tiles, if there is any releasing agent on the back, clean it with brush. The surface temperature should be between 5°C and 35°C. The surfaces also should be structurally sound, dry, clean and free of grease, oil, dirt,

chemical agents such as sealers or curing compounds. Rough or uneven concrete surface should be made smooth with cement underlayment to provide the required finish. The dry concrete substrate with high water absorption rate should be dampened and the excessive water should be wiped off before installation.

INSTALLATION

1) Mixing

Based on the mixing ratio powder: water = 4.3:1 (weight ratio), carefully pour the required amount of clean water into a clean mixing container and slowly add the mortar powder. Mix with a low-speed mixer (about 350rpm) to a smooth, creamy paste consistency. Allow the mortar to slake in the container for 5-10 minutes and remix. Mix occasionally to keep mix fluffy without adding more water and powder.

2) Application

Use a suitable sized notched trowel with sufficient depth to ensure full bedding of the tile. For the large tiles (>300*300mm), back butter to reach full bedding.

Apply mortar by using the flat side of the trowel to the substrate with pressure. Apply additional mortar and comb it in a single direction with the trowel notched side.

Place the tiles into the wet mortar and beat in using a rubber mallet or tile vibrator to press tile to help achieve maximum coverage. Ensure proper contact between mortar, tile and substrate by periodically removing a few tiles to inspect for acceptable coverage. If mortar is skinned over, remove and replace with fresh mortar.

Remove excess mortar from the joints so that at least 2/3 of the tile depth is available for grouting.

3) Cleaning

Clean hands, tools and tile surface while mortar is fresh.

4) Protection

Protect from traffic for 24 hours. Protect from frost and rain for 7 days

CAUTION:



Contains Portland cement. If any cement or cement mixtures get into eye, flush immediately and repeatedly with water and consult a physician promptly. Freshly mixed cement, concrete or grout may cause skin injury. Avoid contact with skin where possible and wash exposed areas promptly with water.

WARRANTY:

The liability of TM is limited to the replacement of its products containing manufacturing defects. The foregoing warranty constitutes the sole liability of TM with respect to this product, and is in lieu of and excludes all other conditions, warranties, guarantees, obligations, rights or representations (including any warranties of merchantability, fitness or durability), whether expressed or implied and whether arising by operation of law or otherwise. TM shall not be liable for any damages whatsoever, including any damages for negligence or fundamental breach or for personal injury or property damage, direct, or indirect, consequential or special, resulting from or alleged to have resulted from the use of or the inability to use the product. No representative of TM or any other person or entity has any authority whatsoever to assume any other warranty on behalf of TM. This warranty may not be modified or amended.

AVAILABILITY AND PRICE

AVAILABILITY

TM products are available worldwide.

For distributor information:

Tel: 905-275-7545

Email: info@tammycanada.com

PRICE

Contact a TM representative / Authorized dealer in your area.

TECHNICAL SERVICE

TECHNICAL ASSISTANCE

Information is available by calling the TM Technical Service at:

Tel: 905-275-7545

Email: info@tammycanada.com

TDS AND SDS

TDS and SDS are available on TM website:

www.tammycanada.com